



RE-TIRE SHADES OF BLACK RECYCLED RUBBER ROLLS AND TILE

TECHNICAL DATA SHADES OF BLACK COLLECTION: 20% or LESS COLOR

(TECHNICAL DATA FOR BASICS, KALEIDOSCOPE, MEDLEY COLORS IS AVAILABLE ON DOCUMENT RT403C)

Data	ASTM / Standard	Results
Density	D-792	60lbs cu. Ft.
Shore Hardness A Durometer	D-2240	60 +/- 5
Taber Abrasion	C-501	0.45
Coefficient of friction	D-2047	.83 Dry - .98 Wet
Static Load	F-970	.001
Compression Set	D-395B	12% or less
Aging Resistance	D-750	No Change
Ozone Exposure	D-1149-86	No Adversities
Smoke Developed	E-84	Passes 250
Flame Spread	E-84	125
Tensile	D-412	150 psi
Electrostatic Propensity	AATCC Test Method 134	Neg 0.4 KV
Flexibility	F-137	Passes 6mm Mandrel
Static Dissipation	F-150	call for test results
VOC Compliance	D-5116 (modified)	complied
TOLERANCES		
Width		+/- 1/4"
48" rolls		Cut at 48.5"
Thickness		+/- .020
36" x 36" Tiles		+/- .078

Chemical Resistance:

5% Ammonia – No Change	5% Phenol – No Change
Bleach – No Change	Gasoline – No Change
5% Acetic Acid – No change	Sulfuric Acid – No Change
70% Isopropyl Alcohol – No Change	Kerosene – No Change
Mineral Oil – No Change	Olive Oil – No Change
5% Hydrochloric Acid – No Change	5% Sodium Hydroxide – No Change

Granulate: 1-3 mm EDPM: Black 8/16 SBR

Binder: Urethane

Standard roll width: 48"

Standard tile: 36" x 36"

Standard thickness: 4, 6, 9 mm

Skive/Knife marks on product is an inherent characteristic of re-cycled rubber and are not to be viewed as a reason for rejecting product. Every effort is made to offer consistency in size, color and density within a lot. Slight variations are possible from lot to lot.